

Compared with the conventional nylons, ERTALON 4.6 (STANYL®) features a better retention of stiffness and creep resistance over a wide range of temperatures as well as a superior heat ageing resistance. Therefore, applications for ERTALON 4.6 are situated in the "higher temperature area" (80 - 150°C) where stiffness, creep resistance, heat ageing resistance, fatigue strength and wear resistance of PA 6, PA 66, POM and PET fall short.

Physical properties (indicative values*)

PROPERTIES	Test methods ISO/(IEC)	Units	VALUES
Colour	—	—	reddish brown
Density	1183	g/cm ³	1.18
Water absorption:			
– after 24/96 h immersion in water of 23°C (1)	62	mg	90/180
	62	%	1.30/2.60
– at saturation in air of 23°C / 50% RH	—	%	2.8
– at saturation in water of 23°C	—	%	9.5
Thermal Properties (2)			
Melting temperature	—	°C	295
Thermal conductivity at 23°C	—	W/(K·m)	0.30
Coefficient of linear thermal expansion:			
– average value between 23 and 60°C	—	m/(m·K)	80·10 ⁻⁶
– average value between 23 and 100°C	—	m/(m·K)	90·10 ⁻⁶
Temperature of deflection under load:			
– method A: 1.8 MPa	+ 75	°C	160
Max. allowable service temperature in air:			
– for short periods (3)	—	°C	200
– continuously: for 5,000/20,000 h (4)	—	°C	155/135
Min. service temperature (5)			-40
Flammability (6):			
– "Oxygen Index"	4589	%	24
– according to UL 94 (3/6 mm thickness)	—	—	HB/HB
Mechanical Properties at 23°C (7)			
Tension test (8):			
– tensile stress at yield (9)	+ 527	MPa	100
	++ 527	MPa	55
– tensile strain at break (9)	+ 527	%	25
	++ 527	%	> 100
– tensile modulus of elasticity (10)	+ 527	MPa	3,300
	++ 527	MPa	1,300
Compression test (11):			
– compressive stress at 1/2/5% nominal strain (10)	+ 604	MPa	23/45/94
Creep test in tension (8):			
– stress to produce 1% strain in 1,000 h ($\sigma_{1/1,000}$)	+ 899	MPa	22
	++ 899	MPa	7.5
Charpy impact strength – Unnotched (12)	+ 179/1eU	kJ/m ²	no break
Charpy impact strength – Notched	+ 179/1eA	kJ/m ²	8
Izod impact strength – Notched	+ 180/2A	kJ/m ²	8
	++ 180/2A	kJ/m ²	25
Ball indentation hardness (13)	+ 2039-1	N/mm ²	165
Rockwell hardness (13)	+ 2039-2	—	M 92
Electrical Properties at 23°C			
Electric strength (14)	+ (60243)	kV/mm	25
	++ (60243)	kV/mm	15
Volume resistivity	+ (60093)	Ω·cm	> 10 ¹⁴
	++ (60093)	Ω·cm	> 10 ¹²
Surface resistivity	+ (60093)	Ω	> 10 ¹³
	++ (60093)	Ω	> 10 ¹²
Relative permittivity ϵ_r :			
– at 100 Hz	+ (60250)	—	3.8
	++ (60250)	—	7.4
– at 1 MHz	+ (60250)	—	3.4
	++ (60250)	—	3.8
Dielectric dissipation factor tan δ :			
– at 100 Hz	+ (60250)	—	0.009
	++ (60250)	—	0.13
– at 1 MHz	+ (60250)	—	0.019
	++ (60250)	—	0.06
Comparative tracking index (CTI)	+ (60112)	—	400
	++ (60112)	—	400

Note: 1 g/cm³ = 1,000 kg/m³; 1 MPa = 1 N/mm²; 1 kV/mm = 1 MV/m

Availability

Round Rods: Ø 5-60 mm - **Plates:** Thicknesses 10-50 mm

All information supplied by or on behalf of Quadrant Engineering Plastic Products in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Quadrant Engineering Plastic Products assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Quadrant Engineering Plastic Products for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.

Legend

+ : values referring to dry material
 ++ : values referring to material in equilibrium with the standard atmosphere 23°C/50 % RH (mostly derived from literature)

- According to method 1 of ISO 62 and done on discs Ø 50 x 3 mm.
- The figures given for these properties are for the most part derived from raw material supplier data and other publications.
- Only for short time exposure (a few hours) in applications where no or only a very low load is applied to the material.
- Temperature resistance over a period of 5,000/20,000 hours. After these periods of time, there is a decrease in tensile strength of about 50% as compared with the original value. The temperature values given here are thus based on the thermal-oxidative degradation which takes place and causes a reduction in properties. Note, however, that, as for all thermoplastics, the maximum allowable service temperature depends in many cases essentially on the duration and the magnitude of the mechanical stresses to which the material is subjected.
- Impact strength decreasing with decreasing temperature, the minimum allowable service temperature is practically determined by the extent to which the material is subjected to impact. The value given here is based on unfavourable impact conditions and may consequently not be considered as being the absolute practical limit.
- These estimated ratings, derived from raw material supplier data, are not intended to reflect hazards presented by the materials under actual fire conditions. There is no UL-yellow card available for ERTALON 4.6 stock shapes.
- The figures given for the properties of dry material (+) are for the most part average values of tests run on test specimens machined out of rods Ø 40-60 mm.
- Test specimens: Type 1 B.
- Test speed: 20 mm/min.
- Test speed: 1 mm/min.
- Test specimens: cylinders Ø 12 x 30 mm.
- Pendulum used: 15 J.
- 10 mm thick test specimens.
- Electrode configuration: 25/75 mm coaxial cylinders; in transformer oil according to IEC 60296; 1 mm thick test specimens.

• This table is a valuable help in the choice of a material. The data listed here fall within the normal range of product properties. **However, they are not guaranteed and they should not be used to establish material specification limits nor used alone as the basis of design.**