

This compression moulded material is similar in composition to TORLON 4301 PAI, and is selected when larger shapes are required.

## Physical properties (indicative values\*)

PROPERTIES	Test methods ISO/(IEC)	Units	VALUES (10)
Colour	—	—	black
Density	1183	g/cm <sup>3</sup>	1.45
Water absorption:			
- after 24 h immersion in water of 23°C (1)	62	mg	26
	62	%	0.30
- at saturation in air of 23°C / 50% RH	—	%	1.9
- at saturation in water of 23°C	—	%	3.8
<b>Thermal Properties</b>			
Melting temperature	—	°C	NA
Glass transition temperature	—	°C	280
Thermal conductivity at 23°C	—	W/(K·m)	0.54
Coefficient of linear thermal expansion:			
- average value between 23 and 100°C	—	m/(m·K)	25·10 <sup>-6</sup>
- average value between 23 and 150°C	—	m/(m·K)	25·10 <sup>-6</sup>
- average value above 150°C	—	m/(m·K)	25·10 <sup>-6</sup>
Temperature of deflection under load:			
- method A: 1.8 MPa	75	°C	280
Max. allowable service temperature in air:			
- for short periods (2)	—	°C	270
- continuously: for min. 20,000h (3)	—	°C	250
Flammability (4):			
- "Oxygen index"	4589	%	44
- according to UL 94 (1.5/3 mm thickness)	—	—	V-0/V-0
<b>Mechanical Properties at 23°C</b>			
Tension test (5):			
- tensile stress at break (6)	527	MPa	80
- tensile strain at break (6)	527	%	5
- tensile modulus of elasticity (7)	527	MPa	5,800
Compression test (8):			
- compressive stress at 1% nominal strain (7)	604	MPa	31
- compressive stress at 2% nominal strain (7)	604	MPa	58
Charpy impact strength - Notched	179/1eA	kJ/m <sup>2</sup>	4
Ball indentation hardness (9)	2039-1	N/mm <sup>2</sup>	200
Rockwell hardness (9)	2039-2	—	M 105
<b>Electrical Properties at 23°C</b>			
Volume resistivity	(60093)	Ω·cm	> 10 <sup>13</sup>
Surface resistivity	(60093)	Ω	> 10 <sup>13</sup>
Relative permittivity ε <sub>r</sub> :			
- at 100 Hz	(60250)	—	6.0
- at 1 MHz	(60250)	—	5.4
Dielectric dissipation factor tan δ :			
- at 100 Hz	(60250)	—	0.037
- at 1 MHz	(60250)	—	0.042

Note: 1 g/cm<sup>3</sup> = 1,000 kg/m<sup>3</sup>; 1 MPa = 1 N/mm<sup>2</sup>; 1 kV/mm = 1 MV/m

NA: not applicable

### Legend

- (1) According to method 1 of ISO 62 and done on discs Ø 50 x 3mm.
- (2) Only for short time exposure (a few hours) in applications where no or only a very low load is applied to the material.
- (3) Temperature resistance over a period of min. 20,000 hours. After this period of time, there is a decrease in tensile strength of about 50% as compared with the original value. The temperature value given here is thus based on the thermal-oxidative degradation which takes place and causes a reduction in properties. Note, however, that the maximum allowable service temperature depends in many cases essentially on the duration and the magnitude of the mechanical stresses to which the material is subjected.
- (4) These mostly estimated ratings, derived from raw material supplier data, are not intended to reflect hazards presented by the materials under actual fire conditions. There is no UL-yellow card available for TORLON 4501 PAI stock shapes.
- (5) Test specimens: Type 1 B.
- (6) Test speed: 5 mm/min.
- (7) Test speed: 1 mm/min.
- (8) Test specimens: cylinders Ø 12 x 30 mm.
- (9) 10 mm thick test specimens.
- (10) It has to be noted that the figures given for the properties of this TORLON grade have mainly been derived from tests run on test specimens machined from extruded material.

- This table is a valuable help in the choice of a material. The data listed here fall within the normal range of product properties of dry material. **However, they are not guaranteed and they should not be used to establish material specification limits nor used alone as the basis of design.**

It has to be noted that TORLON 4501 PAI is a filled, and consequently anisotropic material (properties differ when measured parallel and perpendicular to the compression direction).

## Availability

**Round Rods:** Ø 50.80-368.30 mm - **Plates:** Thicknesses 9.53-50.80 mm - **Tubes:** O.D. 42.86-882.65 mm

All information supplied by or on behalf of Quadrant Engineering Plastic Products in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Quadrant Engineering Plastic Products assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Quadrant Engineering Plastic Products for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.